



#4003 FIBERED ROOF RESATURANT & SEALER

TROPICAL ROOFING PRODUCTS' #4003 Fibered Roof Resaturant & Sealer is ready to use as it comes from the can. #4003 is a mixture of penetrating solvents, select asphalt, fortifiers, drying agents, and hardeners that give this superior product exceptional quality. #4003's strong solvent base enables it to penetrate the old mat, rejuvenating it with fresh oils to keep it from drying out and cracking. The drying agents in #4003 cure the asphalt enough to make the roof accessible without giving up the essential ductility of the coating. #4003 forms a continuous durable waterproof seal that will not crack under the harshest of conditions. #4003 exceeds the requirements for ASTM D-4479.

PREPARATION: All surfaces must be clean, dry, smooth, even, and free from all other foreign matter. Raised edges, buckles, and blisters should be cut and flattened. Check flashings, drains, edgings, vents, and valleys and repair as needed.

APPLICATION: Apply to clean dry surface using stiff, bristle brush, roller, or spray equipment. For best results, weather should be at least 65°F, dry and clear, with no threat of rain for 48 hours. Drying time is approximately 48 hours in warm, dry weather.

COVERAGE: Apply at the rate of approximately 35 square feet per gallon, depending on job specifications. Stir coating to uniform consistency before using. Avoid heavy mounds of mass accumulation.

PRECAUTIONS: DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner.

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. USE ONLY WITH ADEQUATE VENTILATION! Avoid contact with skin and breathing of vapor. CLOSE AIR INTAKES on roof until solvents dissipate. KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! Contains volatile solvents that might contaminate potable water.

MAXIMUM V.O.C = 300 G/L
CONSISTENCY — Thick Black Liquid
WEIGHT — 8.8 lbs. per gal
FLASH POINT (T.C.C.) — 105°F+
DRYING TIME — Average: 2-5 hrs. to touch

**ASTM
D-4479**

www.tropicalroofingproducts.com



FLORIDA
1904 SW 31st Ave.
Hallandale, FL 33009
fax: 954.963.2033
toll-free: 800.432.2855

CALIFORNIA
14435 Macaw Street
La Mirada, CA 90638
fax: 714.670.1605
toll-free: 877.827.2622

TEXAS
1225 Brai Drive, P.O. Box 5335
Port Arthur, TX 77640
fax: 409.727.4647
toll-free: 866.727.0091

**MIAMI-DADE COUNTY
APPROVED**
NOA#: 06-0119.03
Exp: 8/23/11