



#365 MODIFIED EMULSION

TROPICAL ROOFING PRODUCTS' #365 Modified Emulsion #365 Modified Asphalt Emulsion is a protective elastomeric and versatile water-based roof and waterproof coating. #365 is a solvent free, all purpose coating ideal for use as a surface coating for built-up roofing, metal, and masonry surfaces, for pipes and tanks above or below ground level, SBS modified and APP modified (torch down). #365 is made from asphalt emulsified with bentonite clay, an acrylic elastomer, and water. #365 is cold applied, corrosion-resistant, and waterproof when dry while also resisting most corrosive fumes and spray. #365 will not run, sag, crack, or "alligator," under the harshest of weather conditions. #365 Modified Asphalt Emulsion provides an excellent surface over which to apply white elastomeric coatings.

PREPARATION: All surfaces must be clean, have proper drainage, and be free from rust, dirt and all other foreign matter. Clean all cracks, holes, and damaged areas, repairing when necessary and allow repairs to thoroughly cure.

APPLICATION: Apply #365 by roofing brush, roller or spray, evenly covering the surface. Two coats are recommended. Allow to dry completely between coats. Dry time is usually 6-24 hours in dry or hot weather conditions. In cool or damp weather drying will be slower, 2-7 days.

COVERAGE: #365 should be applied at a rate of 2 - 3 gallons per 100 square feet, dependent upon roof surface.

PRECAUTIONS: Do not apply when ambient temperature is below 55°F, or if there is a threat of rain, heavy dew, or temperatures below 40°F within 48 hours. Do not heat container or store at temperatures greater than 120°F. Application over hot applied asphalt may not prevent alligatoring. This coating is not recommended over rubber, PVC sheet roofing or old roofs that are too dry and brittle. When transporting this product, be sure the pail is secured and the lid is tight. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

- DO NOT USE IF RAIN IS IMMINENT.
- DO NOT ALLOW #365 TO FREEZE.
- COATING MUST BE DRY BEFORE EXPOSURE TO WATER.

CLEANUP: Fresh coating can be removed with warm water and soap. If material has started to dry, use mineral spirits or paint thinner.

CAUTION: DO NOT TAKE INTERNALLY! KEEP OUT OF REACH OF CHILDREN.

Use protective measures to avoid contact with eyes and skin. If swallowed, CALL PHYSICIAN IMMEDIATELY! In case of eye contact, open eyelids wide and flush immediately with plenty of water for at least 15 minutes. GET MEDICAL ATTENTION! **CAUTION! KEEP OUT OF REACH OF CHILDREN.** Close container after each use. **DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!**

Calif. Prop.65 Chemical Warning (CALIFORNIA HEALTH AND SAFETY CODE #25249.5 ET SEQ) Detectable amounts of some chemicals known to the State of California to cause cancer, birth defects and/or other reproductive harm may be found in various Tropical Roofing Products' petroleum based products and their vapors. Read and follow label directions and information given on Material Safety Data Sheets and use care when handling or using all petroleum products.

MAXIMUM V.O.C = 30 G/L

ASTM D-1227, Type III, Class I

www.tropicalroofingproducts.com



FLORIDA
1904 SW 31st Ave.
Hallandale, FL 33009
fax: 954.963.2033
toll-free: 800.432.2855

CALIFORNIA
14435 Macaw Street
La Mirada, CA 90638
fax: 714.670.1605
toll-free: 877.827.2622

TEXAS
1225 Brai Drive, P.O. Box 5335
Port Arthur, TX 77640
fax: 409.727.4647
toll-free: 866.727.0091