



# #101 ALL WEATHER PLASTIC CEMENT

**TROPICAL ROOFING PRODUCTS' #101 ALL WEATHER PLASTIC CEMENT** is a professional grade asphaltic base plastic cement. #101 is ready to use as it comes out of the can and can be applied with a trowel or knife. #101 is a carefully mixed homogeneous blend of high-grade fibers, select asphalt, minerals, plasticizers, and aromatic hydrocarbons. #101 readily adheres to all prepared surfaces and will not sag, slip, or mudcrack, and will remain highly resilient and durable through all seasons. #101 is a multipurpose plastic cement for repairing leaks, cracked spots, holes in shingles, concrete, and steel or metal roofs. #101 can be used on all flashings around skylights, gutters, and in all crevices.

**PREPARATION:** Surface must be clean and free from rust or any other foreign matter that would interfere with a good bond. Remove rust with a wire brush. For best results in cold weather, store at room temperature for 24 hours prior to application.

**APPLICATION:** Use a trowel, putty knife or gloved hand to repair cracks, tears, holes, and breaks by applying cement 1/8" to 1/4" thick. Apply and work cement into break or crack, then apply cement 2"-4" beyond the problem area feathering the edges. Embed glass fabric to reinforce cement, then cover with additional cement, if problem area is over 1/4" wide or 2" long.

**COVERAGE:** Apply at a minimum rate of 1/8". Approximate coverage is 12 square feet per gallon.

**PRECAUTIONS:** DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

**CLEANUP:** Clean tools with mineral spirits or paint thinner.

### CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. USE ONLY WITH ADEQUATE VENTILATION! Avoid contact with skin and breathing of vapor. CLOSE AIR INTAKES on roof until solvents dissipate. KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! Contains volatile solvents that might contaminate potable water.

#### MAXIMUM V.O.C = 250 G/L

CONSISTENCY — Thick Mastic, Apply by Trowel  
WEIGHT — 8.8 lbs. per gal  
FLASH POINT (T.C.C.) — 105°F+  
SERVICE TEMPERATURE (Range) — 40°F-90°F  
RESISTANCE TO ACIDS, ALKALYS — Excellent

ASTM  
D-4586  
D-3409

[www.tropicalroofingproducts.com](http://www.tropicalroofingproducts.com)



FLORIDA  
1904 SW 31st Ave.  
Hallandale, FL 33009  
fax: 954.963.2033  
toll-free: 800.432.2855

CALIFORNIA  
14435 Macaw Street  
La Mirada, CA 90638  
fax: 714.670.1605  
toll-free: 877.827.2622

TEXAS  
1225 Brai Drive, P.O. Box 5335  
Port Arthur, TX 77640  
fax: 409.727.4647  
toll-free: 866.727.0091

