



#2100



ALL WEATHER PREMIUM

RUBBERIZED FLASHING CEMENT

TROPICAL ASPHALT's #2100 All Weather Premium Rubberized Flashing Cement is an unsurpassed, top notch flashing compound. #2100 is manufactured with high-grade oxidized asphalts for a true cure. #2100 remains resilient and flexible with its high SBS rubber content. Special surfactants make this product adhere to any solid surface in any climate – wet or dry. There are no fillers or extenders of any type. #2100 will not run, slip, sag or mudcrack under any conditions.

PREPARATION: Surface must be clean and free from rust or any other foreign matter that would interfere with a good bond. Remove rust with a wire brush. For best results in cold weather, store at room temperature for 24 hours prior to application.

APPLICATION: Use a trowel, putty knife or gloved hand to repair cracks, tears, holes, and breaks by applying cement 1 / 8 " to 1 / 4" thick. Apply and work cement into break or crack, then apply cement 2" – 4" beyond the problem area feathering the edges. Embed glass fabric to reinforce cement, then cover with additional cement, if problem area is over 1/4" wide or 2" long.

COVERAGE: Apply at a minimum rate of 1/8" (32mm). Approximate coverage 12 - 20 square feet per gallon.

PRECAUTIONS: DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner.

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. **USE ONLY WITH ADEQUATE VENTILATION!** Avoid contact with skin and breathing of vapor. **CLOSE AIR INTAKES** on roof until solvents dissipate. **KEEP OUT OF REACH OF CHILDREN.** Close container after each use. **DO NOT TAKE INTERNALLY!** If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY!** Contains volatile solvents that might contaminate potable water.

MAXIMUM V.O.C = 250 G/L



CONSISTENCY.....Thick Mastic, Apply by Trowel
WEIGHT.....8.7 lbs. per gal
FLASH POINT (T.C.C.).....105°F+
SERVICE TEMPERATURE (Range).....40°F - 100°F
RESISTANCE TO ACIDS, ALKYDS.....Excellent



14435 Macaw Street
La Mirada, CA 90638
714-739-1408 * FAX 714-670-1605
Toll Free 1-877-827-2622

1904 S. 31st Avenue
Hallandale, Florida 33009
954-983-3434 ~ FAX: 954-963-2033
Toll Free: 1-800-432-2855

1225 Brai Drive ~ P. O. Box 5335
Port Arthur, Texas 77640
409-727-0091 ~ 409-727-4647 FAX
Toll Free 866-727-0091

www.tropicalasphalt.com