



TROPICAL ASPHALT

#2200 ALUMINUM FLASHING CEMENT ASBESTOS FREE

TROPICAL ASPHALT's #2200 Aluminum Flashing Cement Asbestos Free is a top notch, superior grade, flashing compound that adheres to all surfaces. #2200's unique formulation is manufactured for the professional contractor who demands the best in materials. #2200 is a carefully mixed homogeneous blend of high-grade aluminum pigment, fibers, select asphalt, minerals, plasticizers, and aromatic hydrocarbons. #2200 is ready to use as it comes out of the can. #2200 can be applied with a trowel, knife or gloved hand. #2200 will cure to be a durable resilient cement of excellent adhesion and unsurpassed. #2200 meets and exceeds all specification requirements of ASTM D4586-93 and D-3019-94.

PREPARATION: Surface must be clean, dry and free from rust or any other foreign matter that would interfere with a good bond. Remove rust with a wire brush. For best results in cold weather, store at room temperature for 24 hours prior to application.

APPLICATION: Use a trowel or putty knife to repair cracks, tears, holes, and breaks by applying cement 1 / 8 " to 1 / 4" thick. Apply and work cement into break or crack, then apply cement 2" – 4" beyond the problem area feathering the edges. Embed glass fabric to reinforce cement, then cover with additional cement, if problem area is over 1/4" wide or 2" long.

COVERAGE: Apply at a minimum rate of 1/8" (32mm). Approximate coverage 12 - 13 square feet per gallon.

PRECAUTIONS: DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner.

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from direct heat and flame. **USE ONLY WITH ADEQUATE VENTILATION!** Avoid contact with skin and breathing of vapor. **CLOSE AIR INTAKES** on roof until solvents dissipate. **KEEP OUT OF REACH OF CHILDREN.** Close container after each use. **DO NOT TAKE INTERNALLY!** If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY!** Contains volatile solvents that might contaminate potable water.

V. O. C. = 250 grams per liter

CONSISTENCY.....Thick Bright Aluminum Mastic	FLASH POINT.....105°F+
DRY TIME.....Dries: 4 hours Cures: 2 weeks	SERVICE TEMPERATURE (Range).....30°F - 100°F
WEIGHT.....9.75 lbs. per gal	RESISTANCE TO ACIDS, BASES.....Excellent

14435 Macaw Street
La Mirada, CA 90638
714-739-1408 ~ FAX 714-670-1605
Toll Free 1-877-827-2622

1904 S. 31st Avenue
Hallandale, Florida 33009
954-983-3434 ~ FAX: 954-963-2033
Toll Free: 1-800-432-2855

1225 Brai Drive ~ P. O. Box 5335
Port Arthur, Texas 77640
409-727-0091~409-727-4647FAX
Toll Free 866-727-0091