



# TROPICAL ASPHALT

## #367 NEOPRENE MODIFIED EMULSION

**TROPICAL ASPHALT #367 Neoprene Modified Emulsion** is a tough, durable, fiberglass reinforced, neoprene modified, elastomeric, versatile, water-based roof and waterproof protective coating. #367 is a solvent free, all purpose coating ideal for use as a surface coating for built up roofing, metal, and masonry surfaces, for pipes and tanks above or below ground level, SBS modified and APP modified (torch down). #367 is made from asphalt emulsified with fiberglass, specialty neoprene modifier, bentonite clay and water. #367 is cold applied, corrosion-resistant, non-flammable while wet, and waterproof when dry, while also resisting most corrosive fumes and spray. #367 will not run, sag, crack, or "alligator," under the harshest of weather conditions. #367 Neoprene Modified Emulsion provides an excellent surface over which to apply white elastomeric coatings. Complies with ASTM 0-1227-95 Type II, Class I. #367 Modified Asphalt Emulsion is available in 5-gallon pails, 55-gallon drums, and 250-gallon totes.

**PREPARATION:** All surfaces must be clean, have proper drainage, and be free from rust, dirt, and all other foreign matter. Remove rust with wire brush. A better bond will result if surface is damp when #367 is applied, but surface must be free of standing water. Clean all cracks, holes and damaged areas, repairing when necessary and allow repairs to thoroughly cure.

**APPLICATION:** Apply #367 by roofing brush, roller, or spray, evenly covering the surface. Two coats are recommended. Allow to dry completely between coats. Dry time is usually 6-24 hours in dry and hot weather conditions. In cool, damp weather drying will be slower, 2 – 7 days.

**COVERAGE:** #367 should be applied at a rate of 2 – 3 gallons per 100 square feet, dependent upon roof surface.

**PRECAUTION:** *DO NOT ALLOW #367 TO FREEZE.* Do not apply when ambient temperature is below 55°F, or if there is a threat of rain, heavy dew, or temperatures below 40°F within 24-48 hours. Do not heat container or store at temperatures greater than 120°F. Application over hot applied asphalt may not prevent alligatoring. This coating is not recommended over gravel, rubber or PVC sheet roofing, or old roofs that are too dry and brittle. When transporting this product, be sure the pail is secured and the lid is tight. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

**CLEAN UP:** Fresh coating can be removed with warm water and soap. If material has started to dry, use mineral spirits or paint thinner.

**CAUTION:** DO NOT TAKE INTERNALLY! KEEP OUT OF REACH OF CHILDREN. Use protective measures to avoid contact with eyes and skin. If swallowed, CALL PHYSICIAN IMMEDIATELY! In case of eye contact, open eyelids wide and flush immediately with plenty of water for at least 15 minutes. GET MEDICAL ATTENTION! Close container after each use.

**MAX V.O.C. 30 grams per liter**

# TROPICAL ASPHALT

14435 Macaw Street  
La Mirada, CA 90638  
714-739-1408 \* FAX 714-670-1605  
Toll Free 1-877-827-2622

1904 S. 31<sup>st</sup> Avenue  
Hallandale, Florida 33009  
954-983-3434 \* FAX: 954-963-2033  
Toll Free: 1-800-432-2855

1225 Brai Drive ~ P. O. Box 5335  
Port Arthur, Texas 77640  
409-727-0091~409-727-4647FAX  
Toll Free 866-727-0091

[www.tropicalasphalt.com](http://www.tropicalasphalt.com)