



#950



ETERNAMASTIC

WHITE ELASTOMERIC ROOF COMPOUND

TROPICAL ASPHALT's # 950 ETERNAMASTIC is a tough, tenacious and durable white compound manufactured by Tropical Asphalt with high grade components. #950 ETERNAMASTIC was developed and is designed to be a superior reflective material for new roofing, re-roofing and roof maintenance markets. #950 ETERNAMASTIC is user friendly and can be applied using a brush, putty knife or trowel. #950 ETERNAMASTIC's high pigment level provides superior hiding power.

BENEFITS:

Reflective, Easy to apply, Product toughness and durability, Elasticity, Compatibility, Superior hiding power

PRODUCT APPLICATION INCLUDES:

Laps, Cracks, Seams, Directional wall changes, Screw heads, Roof intrusions

PRETREATMENT: Treat all surfaces with the appropriate ETERNALASTIC primer.

COVERAGE: 25-30 linear feet per gallon with 4" to 6" wide application.

CURE: Cures by ultra violet rays; allow for sufficient daylight. Cure time affected by environmental conditions.

STORAGE: In a clean, warm and well-ventilated area. Storage area temperature must be above 45°F.

CLEANUP: Clean tools with mineral spirits or paint thinner, if compound has dried. If compound is still wet, clean up with warm soapy water.

PRECAUTIONS: **DO NOT APPLY IF TEMPERATURE IS BELOW 55° F or above 110°F. DO NOT APPLY IF THERE IS A THREAT OF RAIN OR DEW WITHIN 48-72 HOURS.** Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur. **DO NOT ALLOW PRODUCT TO FREEZE.** Do not heat container or store at temperatures greater than 120°F.

CAUTION!

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY!
If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY!**

PHYSICAL PROPERTIES

Color: White

Percent Solids, Weight: 67.8%

Percent Solids, Volume: 60.0%

Weight Per Gallon: 11.0 lbs.

Viscosity (Stormer): 240 KU

Elongation: 560%

Recovery: 94%

Application: Brush, Putty Knife or Trowel

Tensile Strength: 213 psi

Shelf Life: 12 months (at recommended conditions)

MAXIMUM V.O.C = 15 G/L

14435 Macaw Street

La Mirada, CA 90638

714-739-1408 * FAX 714-670-1605

Toll Free 1-877-827-2622

1904 S. 31st Avenue

Hallandale, Florida 33009

354-983-3434 ~ FAX: 954-963-2033

Toll Free: 1-800-432-2855

1225 Brai Drive ~ P. O. Box 5335

Port Arthur, Texas 77640

409-727-0091 ~ 409-727-4647 FAX

Toll Free 866-727-0091

www.tropicalasphalt.com