



#972



SEBS ELASTOMERIC ROOF COATING

TROPICAL ASPHALT's #972 SEBS Elastomeric Coating is a single component block copolymer elastomeric fluid applied coating. The coating needs no intermixing is easy to apply and has excellent surface appearance. #972 SEBS Elastomeric Coating provides excellent elongation properties, cold weather pliability, chemical, weather and water resistance.

USES: #972 SEBS Elastomeric Coating may be applied to metal, steel, concrete, aluminum, brick, polyurethane, wood and fiberglass surfaces. The coating also can be used to re-coat existing acrylic or polyurethane coatings and most painted surfaces. #972 SEBS Elastomeric Coating may be applied to APP, SBS, and BUR roofing.

PREPARATION: All surfaces to be coated must be clean, dry, and free from dirt, oil, grease and rust. Newly poured concrete must cure a minimum of 30 days prior to application of #972. Metal and wood must be primed with Elastomeric Primer at the rate of ½ to ¾ gallon per 100 square feet.

APPLICATION: Recommended application for #972 SEBS Elastomeric Coating is by brush, spray or roller. Apply 2 gallons per 100 square feet in two applications (1 gallon of base and 1 gallon of top coating). Allow base coat (Stain Blocker) to cure thoroughly prior to application of the finish coat. Apply at temperature 45°F and rising. Curing will take 12 to 24 hours dependent upon ambient temperatures and humidity.

CARE OF EQUIPMENT: Equipment and tools may be cleaned with petroleum solvents, mineral spirits or paint thinner. Take necessary precautions when handling combustible material.

PRECAUTIONS: Keep away from heat, sparks and open flame. In interior areas provide for proper ventilation or respiratory equipment. Use proper safety equipment.

WARNING: Avoid breathing fumes and prolonged contact with skin. Do not take internally. **DANGER!** Harmful or fatal if swallowed. Do not induce vomiting. Call a physician immediately. Keep container covered when not in use. Do not thin. **DO NOT HEAT CONTAINER** or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CAUTION!

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY!
If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

MAXIMUM V.O.C = 550 G/L

14435 Macaw Street
La Mirada, CA 90638
714-739-1408 * FAX 714-670-1605
Toll Free 1-877-827-2622

1904 S. 31st Avenue
Hallandale, Florida 33009
954-983-3434 ~ FAX: 954-963-2033
Toll Free: 1-800-432-2855

1225 Brai Drive ~ P. O. Box 5335
Port Arthur, Texas 77640
409-727-0091 ~ 409-727-4647 FAX
Toll Free 866-727-0091

www.tropicalasphalt.com